

Concreto ligero Light concrete



OFICINAS CORPORATIVAS

Azahares No. 26 Desp. 203 Col. Santa María Insurgentes C.P.: 06430, México D.F. Tel: (52)-(55) 1946.0850 5583.0557 mail: info@metapol.com.mx

HEADQUARTERS

Azahares No. 26 Desp. 203 Col. Santa Maria Insurgentes Z.C.: 06430, México D.F. Ph: (52)-(55) 1946.0850 5583.0557 mail: info@metapol.com.mx

PLANTA

Carretera a Veracruz Km.144 San Cosme Xaloztoc Tlaxcala, México C.P.: 90460 Tel: (241) 413.0126 Fax: (241) 413.0156

PLANT

Carretera a Veracruz Km.144 San Cosme Xaloztoc Tlaxcala, México Z.C.; 90460 Ph: (241) 413.0126 Fax: (241) 413.0156









metapol.com.mx



PRODUCTS

GAP LINE

PRODUCT	TYPE	FORM	D-50	%NV	L/NL
GAP LCG 95	Powder	Flake	38	95%	L
GAP LCM 95			30	95%	L
GAP LFC-2	Paste		18	70%	L
GAP LCM-2			35	70%	L

RECOMMENDED APPLICATIONS

To achieve a better application with the aluminum pigments, the following conditions should be met:

- Pre-dampening with the selected system promotes particles separation. (It is advisable at a ratio of 1:1 or 1:2 pigment and system, period of time from 5 to 15 minutes).
- Dispersion should be made with disk or propeller agitators; since serrated or bladed agitators produce shear stress damaging the aluminum particles which may result in changes in the original distribution pattern, hence modifying the pore size of the finished product. Stir at low speed, at or below 400 rpm.
- Use fresh batches; expired materials may cause agglomeration and a modified particle distribution, resulting in large pores, reducing resistance of manufactured materials.
- Dispersion of product might be improved by applying a surfactant compatible with your system.

NOTES

- * Prior to use and application of this product, consult the technical data sheet to consider other technical requirements and safety precautions.
- *The information provided corresponds to the current technology, knowledge and experience. All the indications are given as guiding information and / or advice, so that METAPOL, S.A. DE C.V., disclaims any liability for its misuse.

