



PIGMENTOS METÁLICOS  
METALLIC PIGMENTS

PIGMENTOS DE ALUMINIO Y BRONCE  
ALUMINUM AND BRONZE PIGMENTS

## Pinturas decorativas Decorative Coatings

*Together creating  
a brilliant world*

#### OFICINAS CORPORATIVAS

Azahares No. 26 Desp. 203  
Col. Santa María Insurgentes  
C.P.: 06430, México D.F.  
Tel: (52)-(55) 1946.0850  
5583.0557  
mail: info@metapol.com.mx

#### HEADQUARTERS

Azahares No. 26 Desp. 203  
Col. Santa María Insurgentes  
Z.C.: 06430, México D.F.  
Ph: (52)-(55) 1946.0850  
5583.0557  
mail: info@metapol.com.mx

#### PLANTA

Carretera a Veracruz Km.144  
San Cosme Xaloztoc  
Tlaxcala, México  
C.P.: 90460  
Tel: (241) 413.0126  
Fax: (241) 413.0156

#### PLANT

Carretera a Veracruz Km.144  
San Cosme Xaloztoc  
Tlaxcala, México  
Z.C.: 90460  
Ph: (241) 413.0126  
Fax: (241) 413.0156



[metapol.com.mx](http://metapol.com.mx)



# DECORATIVE COATINGS

## PRODUCTS

### ALU LINE

PRODUCT	TYPE	FORM	D-50	%NV
Alu M2040	Paste	Mix	40	63%
Alu M0020	Paste		20	62%
Alu D1060	Paste	Silver Dollar	60	70%
Alu D1054	Paste		54	70%
Alu D2034	Paste		34	70%
Alu D3027	Paste		27	70%

### GAP LINE

PRODUCT	TYPE	D-50	%NV	Solvent
Gap 2	Leafing Paste	22	65%	Aliphatic
Gap 275		22	75%	
Gap 3		17	65%	

### CD LINE

PRODUCT	TYPE	D-50	%NV	Solvent
CD 1525	Leafing Dispersion	22	65%	Aliphatic-Aromatic

### CUBRIO LINE

PRODUCT	TYPE	D-50	%NV	TONE
U 2530	Leafing powder	48-53	100%	Rich Gold,
B 4555		37-44	100%	Rich Pale Gold,
R 7080		20-25	100%	Pale Gold and Copper

### COLORED BRONZE POWDERS

PRODUCT	TYPE	D-50	%NV	TONE
U 2530	Leafing powder	48-56	100%	Royal Lemon, English Green, Ducat, Old Gold, Mandarin, Fire Red, Wine, Lavender
U 3045		48-52	100%	Karat

### SIO-BRIO LINE

PRODUCT	TYPE	FORM	D-50	%NV	L/NL
SIO D5570 WHS	Paste	Dollar	55	70%	NL
SIO D4470 WHS	Paste	Dollar	44	70%	NL
SIO D3670 WHS	Paste	Dollar	36	70%	NL
SIO F2370 WHS	Paste	Flake	23	70%	NL
U 5085 WHS*	Paste	Flake	50	85%	NL
B 3285 WHS*	Paste	Flake	32	85%	NL

\* Available in Rich Gold and Pale Gold tones

### ALU LINE - WATER BASED

PRODUCT	FORM	D-50	%NV	Recommended pH
Alu D1060 WHR	Dollar	60	65%	5-9
Alu D1050 WHR	Dollar	50	65%	
Alu D2036 WHR	Dollar	36	65%	
Alu M1050 WH-4	Mix	50	65%	
Alu F2030 WH-4	Flake	30	65%	Neutral, in situ applications
Hydropaste U2530*	Flake	48-53	85%	

\* Available in Rich Gold, Pale Gold, Pale Rich Gold and Copper

## RECOMMENDATIONS FOR USE

- Metallic pigments are directly incorporated into the vehicle by mixing slowly at low speeds of less than 400 rpm using flat disk propellers or dull blades to avoid damaging the flakes, slowly adding the pigment to minimize dust cloud generation.
- Mixing equipment must be kept grounded.
- To obtain stable formulations during storage, the use of vehicles or resins with a low acidity index is recommended to avoid reactions with the metal causing variations in the tone, loss of brightness or even paint gelation or hardening.
- Carrying out pigment stability tests with the vehicle is desirable.
- To achieve a good coverage in the formulation, it is recommended to use 15 to 22% of pigment over the total formulation, however the customer must adjust to their own needs.

## NOTES

\* Prior to use and application of this product, consult the technical data sheet to consider other technical requirements and safety precautions.

\*The information provided corresponds to the current technology, knowledge and experience. All the indications are given as guiding information and / or advice, so that METAPOL, S.A. DE C.V., disclaims any liability for its misuse.

